## Victory General Technology Co.

General Thermoplastic Elastomers OEM / ODM R&D / Manufacturing

# GSE-26X

### HIGH REBOUND LOW SHRINKAGE RATE NICE COMPRESSION SET PERFORMANCE



#### **PROPERTIES**

Property	Unit	Standard	Value
MI (190°C@2.16kg)	g/10min	ASTM D1238	1.0
Density	g/cm³	ASTM D792	0.95 - 1.10
Hardness	Shore A	ASTM D2240	68±2
Tensile Strength	kg/cm²	ASTM D638	96
Elongation	%	ASTM D638	790
Tear Strength	kg/cm	ASTM D624	48
Softening Point	٥С	ASTM D1525	100 - 105

All given data should be considered as a reference guide.

#### **FORMS**

1. Form: Pellets

Color: Natural (White)
Packaging: 25 kg/bag





#### **FEATURES**

- 1. Highly compatible with all kinds of rubber and plastics.
- 2. Suitable for peroxide crosslink system.
- 3. It's excellent with adhesive property and resilience.
- Produce products with physical properties similar to natural rubber and synthetic rubber foaming products, and also is recyclable and has low shrinkage rate and enhances compression set.

#### **APPLICATIONS**

Sports and leisure, footwear soles, safety protection products and other products which acquires high rebound and good compression set.

#### **CERTIFICATIONS**

SGS 8 Heavy Metals Free, Report No. TE/2020/10016

#### **STORAGE**

- 1. Keep in cool place without being exposed to direct sunlight. Store it at temperature below 50°C.
- Keep out of fire and heat.
- 3. For better storage, keep the packaging sealed if unused up.

Version 2. 2020.01.02

**TEL:** +886-4-24711219 **ADD:** 10F-5, No.131, Sec 2, Wu Chung W. Rd, Taichung, Taiwan R.O.C. **Email:** info@victorygeneral.com **Website:** www.victorygeneral.com